



Registered ISO 9001:2000

PRELIMINARY TECHNICAL DATA

**MP60
ULTRA HIGH PURITY ACRYLIC ADHESIVE**

DESCRIPTION

MP60 is a high purity acrylic adhesive that has been widely used in the hard disk drive industry for many bonding and sealing application. MP60 meets the critical out gassing requirements of the disk drive industry. MP60 has also been approved for trans-dermal drug delivery applications.

The MP60 adhesive is available as a free film transfer adhesive or in various single-sided and double-sided constructions. MD60 adhesive is typically supplied with low extractable silicone polyester liners that meet the extractable silicone requirements of the disk drive industry.

TYPICAL PERFORMANCE DATA [2 mils MP60 adhesive on 2 mil polyester backing]

	<u>From Steel</u>	<u>From E-Coat</u>	<u>From Aluminum</u>
180-DEGREE PEEL ADHESION (PSTC-101)			
15 MINUTE APPLIED (oz./in.)	55-70	50-60	55-75
24 HOURS APPLIED (oz./in.)	70-85	60-75	60-75
STATIC SHEAR (PSTC-107)			
1/2" X 1" 1,000 GRAMS (hours)	>120 hrs		

TYPICAL OUT GASSING	Total Out Gassing	250-400 ng/cm ²
2 mil thick adhesive	Hydrocarbons	< 40 ng/cm ²
IDEMA M11-99 Method	Siloxanes	< 10 ng/cm ²
	Phenols/Alcohols	< 200 ng/cm ²
	Unknowns/Others	< 200 ng/cm ²

NO LOAD APPLIED, SERVICE TEMPERATURE RANGE
-45 DEG. F TO 250 DEG. F CONTINUOUS
-65 DEG. F TO 350 DEG. F SHORT TERM

MINIMUM APPLICATION TEMPERATURE +65 DEGREES. F

NOTE: PERFORMANCE DATA INDICATES TYPICAL VALUES BASED ON LIMITED PRODUCTION AND SHOULD NOT BE USED FOR MINIMUM SPECIFICATION VALUES.

The information contained herein is to the best of our knowledge and belief, accurate. However, since the conditions of handling and of use are beyond our control, we make no guarantee of results and assume no liability for damages incurred by following these suggestions. Nothing contained herein is to be construed as a recommendation for use in violation of any patents or of applicable laws or regulations