



Registered ISO 9001:2008

T E C H N I C A L D A T A

PF-200B-78MO-RP25 (Part # 2119sl)
SINGLE COATED CLEAR POLYESTER FILM

DESCRIPTION

PF200B-78MO-RP25 is a single coated, 2 mil polyester film designed for laminating to polyester urethane foams and sponge rubbers to improve the surface characteristics. PF200B-78MO-RP25 is coated with an aggressive rubber-base adhesive that exhibits excellent adhesion to a wide variety of substrates and has resistance to mild plasticizers. This product should not be used in applications requiring direct exposure to UV light.

TAPE CONSTRUCTION



TYPICAL ADHESIVE PERFORMANCE DATA

PEEL ADHESION (PSTC-101)

Substrate: PP 30 MINUTE APPLIED (oz./in.) 115-135

Substrate: SS 30 MINUTE APPLIED (oz./in.) 100-130

SHEAR ADHESION (PSTC-107)

1" X 1", 1,000 GRAMS, 72 DEGREES F (Hours) 24+

MINIMUM APPLICATION TEMPERATURE 50 DEGREES F

NO LOAD APPLIED, SERVICE TEMP. RANGE -35 TO 150 DEGREES F CONTINUOUS -35 TO 175 DEGREES F SHORT TERM

NOTE: Performance data indicates average production values from stainless steel and should not be used for minimum specification values. It is required that the converter determines suitability of tape prior to use.

DATE: 12/20/10 igc

The information contained herein is to the best of our knowledge and belief, accurate. However, since the conditions of handling and of use are beyond our control, we make no guarantee of results and assume no liability for damages incurred by following these suggestions. Nothing contained herein is to be construed as a recommendation for use in violation of any patents or of applicable laws or regulations.

PF200B-78MO-RP25